

**AMENDMENTS TO THE SPECIFICATION**

**Please delete the present Abstract of the Disclosure.**

**Please add the following new Abstract of the Disclosure:**

A fluoro-resin which does not cause cone break, when used for insulating a core wire having a diameter of 0.05 to 0.07 mm under the conditions of a resin temperature of 320 to 370°C, a drawdown rate [DDR] of 80 to 120, a draw rate balance [DRB] of 1.0, a wire coating speed of 700 feet/minute and an insulating thickness of 30 to 50  $\mu\text{m}$ .